
## DONSTONIE TECHNICAL SPECIFICATION SHEET

Haddonstone Ltd +44 (0) 1604 770711 info@haddonstone.co.uk • Haddonstone (USA) Ltd 866 733 8225 stone@haddonstone.com



It is essential that the base stone is levelled on a continuous mortar bed Foundations designed by others to suit site conditions and loadings ALTERNATIVE

**BASE DETAIL** 

All dimensions exclude joints - allow 6mm  $(\frac{1}{4})$  for bedding joints Hammer action drills must not be used when drilling Haddonstone pieces Unless otherwise stated, all materials other than stonework to be supplied by others

best results the dowel should be grouted with polyester resin or similar (not supplied).

When drilling stonework, use a suitable masonry drill on rotary setting (not hammer action).

BEDDING JOINTS - Pedestal should be bedded and jointed using 1:1:6 cement/lime/sand mortar.

POINTING - Joints should be pointed using our proprietary dry mix pointing material in accordance with the recommended instructions.

Please advise your requirements for dry mix, if any, at time of placing order.

Or use 1:1:6 cement/lime/sand colour-toned to suit (white cement may be necessary).